

TECHNICAL DATA SHEET

Mowiplus D

Characteristics

Mowiplus D is the sodium salt of a polyacrylic acid in aqueous solution, APEO FREE.

Recommended Applications

Wetting and dispersing agent

Specification

These technical data are determined for each lot before its release by our quality control laboratory

Specification	Unit	Value
Solid Content	%	44,0 – 46,0
Viscosity RVT BROOKFIELD (sp.3/50/25°C)	mPa.s	200 – 700
pH Value	-	7,0 – 9,0

This Data is used only to describe the product. There are not subject to constant monitoring or part the specification.

Additional Data	Unit	Value
Density	g/ml	1,20 – 1,30
Appearance		Liquid light brown, slightly cloudy

Applications

Mowiplus Dis used as wetting and / or dispersing agent for inorganic pigments and fillers in emulsion paints with high and medium pvc. Very often it is combined with commercial polyphosphates. It checks to the paints excellent rheology and resistance.

Mowiplus D has an advantageous effect on the storage stability of high pvc paints, thus prevent viscosity increases.

Processing

Compatible with glycol (for dispersions of pigments), acrylic and vinyl emulsions with surfactants anionic and no-ionic.

Paints produed with Mowiplus D present excellent stability during the storage

Mowiplus D promotes intense colors. It allows the preparation of pigment dispersions with high solids contents.

It inhibits the increase of viscosity of the paints that contains starch, even those stored for long period, in high temperatures.

It stabilizes the suspension of such inorganic pigments as china clay, oxide of calcium, hydroxide of aluminium, dioxide of titanium, talc, etc. Ionic character of the solution: anionic.

Compatibility with substances:

- Anionic: good
- No ionic: good
- Cationic: previous experiences are recommended
-

An over dosage of Mowiplus D may affect coagulation of sensible dispersions. Trials must be carried out to determine any incompatibilities in case of significant over dosage. A too high amount of Mowiplus D also influences the water sensibility of emulsion paints in a negative sense.

In the application, through studies, it is observed that the ideal is 0,28% of dispersant on the pigment(solid-on-solid) in a dispersion of dioxide of titanium, type rutilo. In most of the formulations, the addition of 0.2 to 0.5 % of Mowiplus D (solid-on-solid) It satisfies fully, and a dispersant excess is harmful. It should be taken into account the percentage to be used with the dispersion viscosity with several pigments and involved loads.

Preservation and Storage

Mowiplus D should not be stored for longer than 6 months before processing. As far as possible, storage should be at a uniform temperature in the region of 5- 25°C. The product should, in principle, be kept away from frost.

The technical data ascertained by our quality control laboratory at the time of product release may vary according to the storage conditions and may deviate from the stated limits.

Industrial Safety and Environmental Protection

Not a hazardous substance within the meaning of the current Dangerous Substances Regulations (GetStoffV).

A safety data sheet is available on request.

This information corresponds to the present state of our knowledge and is intended as a general description of our products and their possible applications. Archroma makes no warranties, express or implied, as to the information's accuracy, adequacy, sufficiency or freedom from defect and assumes no liability in connection with any use of this information. Any user of this product is responsible for determining the suitability of Archroma's products for its particular application. * Nothing included in this information waives any of Archroma's General Terms and Conditions of Sale, which control unless it agrees otherwise in writing. Any existing intellectual/industrial property rights must be observed. Due to possible changes in our products and applicable national and international regulations and laws, the status of our products could change. Material Safety Data Sheets providing safety precautions, that should be observed when handling or storing Archroma products, are available upon request and are provided in compliance with applicable law. You should obtain and review the applicable Material Safety Data Sheet information before handling any of these products. For additional information, please contact Archroma. * FOR SALES TO CUSTOMERS LOCATED WITHIN THE UNITED STATES AND CANADA THE FOLLOWING APPLIES IN ADDITION: NO EXPRESS OR IMPLIED WARRANTY IS MADE OF THE MERCHANTABILITY, SUITABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE OF ANY PRODUCT OR SERVICE.

© 2013 Archroma